

Amendments to the Claims:

This listing of claims will replace all prior versions and listings of claims in the application.

Listing of Claims:

1. (Original) A micro particle composition comprising nanomagnetic particles distributed within a matrix, wherein the microparticles within the composition have a least one of the following properties: (a) a VAR of at least about 1 Watts/ cm³ under alternating magnetic field conditions suitable for use in a patient; (b) a density of about 2.7 or less; or (c) a size range of about 100 nm to about 200 microns.
2. (Original) A microparticle composition comprising nanomagnetic particles distributed within a matrix, wherein up to 40% of the volume of each microparticle composition is occupied by the constituent magnetic nanoparticles and the microparticles within the composition have at least one of the following properties: (a) a VAR of at least about 10 Watts/cm³ under alternating magnetic field conditions suitable for use in a patient; (b) a density of about 2.7 or less; or (c) a size range of about 100 nm to 200 microns.
3. (Original) A microparticle composition according to claim 2 wherein the volume fraction of nanomagnetic particles in the microparticles is less than 30% of the microparticle composition.

4. (Original) A microparticle composition according to claim 2 wherein the volume fraction of nanomagnetic particles in the microparticles is less than 20% of the microparticle composition.

5. (Original) A microparticle composition according to claim 2 wherein the volume fraction of nanomagnetic particles in the micro particles is less than 15% of the microparticle composition.

6. (Original) A microparticle composition according to claim 2 wherein the volume fraction of nanomagnetic particles in the microparticles is less than 10% of the microparticle composition.

7. (Original) A microparticle composition according to claim 2 wherein the volume fraction of nanomagnetic particles in the microparticles is less than 5% of the microparticle composition.

8. (Currently Amended) A microparticle composition according to ~~anyone of claims 1 to 7~~ to claim 1 wherein the microparticles within the composition have a density of about 2.7 or less.

9. (Currently Amended) A microparticle composition according to ~~anyone of claims 1 to 8~~ claim 1 wherein the microparticles within the composition have a size of about 100 nm to about 200 microns.

10. (Currently Amended) A microparticle composition according to ~~anyone of claims 1 to 9~~ claim 1 wherein the microparticles within the composition have a VAR of about 10 Watts/ cm³ under alternating magnetic field conditions suitable for use in a patient.

11. (Currently Amended) A micro particle composition according to ~~anyone of claims 1 to 10~~ claim 1 wherein the alternating magnetic field is operated at a frequency in the range of about 50-300 kHz and field strength of about 60-120 Oe.

12. (Currently Amended) A microparticle composition according to ~~anyone of claims 1 to 10~~ claim 1 wherein the alternating magnetic field is operated at a frequency in the range of about 100-200 kHz and field strength of about 60 Oe.

13. (Original) A microparticle composition according to claim 11 wherein the alternating magnetic field is operated at a frequency in the range of about 100 kHz and 20 field strength of about 90 Oe.

14. (Currently Amended) A microparticle composition according to ~~anyone of claims 1 to 13~~ claim 1 wherein the nanomagnetic particles distributed within the micro particles are superparamagnetic particles.

15. (Original) A microparticle composition according to claim 14 wherein the superparamagnetic particles are either: (a) ferrites of general formula MO.Fe₂O₃ where M is a bivalent metal such as Fe, Co, Ni, Mn, Be, Mg, Ca, Ba, Sr, Cu, Zn, Pt or mixtures

thereof, or (b) magnetoplumbite type oxides of the general formula MO_6Fe_{203} where M is a large bivalent ion, metallic iron, cobalt or nickel.

16. (Original) A microparticle composition according to claim 15 wherein the superparamagnetic particles are free Fe, Ni, Cr or Co; oxides of Fe, Ni, Cr or Co; or mixtures of Fe, Ni, Cr or Co.

17. (Original) A microparticle composition according to claim 15 wherein the superparamagnetic particles are prepared from iron oxide such as magnetite (Fe_3O_4) or maghemite (γ - Fe_2O_3) and have a size of less than 50 nm.

18. (Original) A microparticle composition according to claim 16 wherein the superparamagnetic particles are maghemite nanoparticles.

19. (Currently Amended) A microparticle composition according to ~~anyone of claims 14 to 18~~ claim 1 wherein the superparamagnetic particles have a size of between 1 nm and 40nm.

20. (Currently Amended) A microparticle composition according to ~~anyone of claims 1 to 19~~ claim 1 wherein the composition is prepared from materials suitable for use in a patient and the particles when delivered to a patient are and placed in an alternating magnetic field are capable of heating tissue in said patient.

21. (Currently Amended) A microparticle composition according to ~~anyone of claims 1 to 19~~ claim 1 wherein the matrix in which the nanoparticles are distributed is a polymer matrix.

22. (Original) A microparticle composition according claim 21 wherein the polymer matrix is suitable for use in human.

23. (Currently Amended) A micro particle composition according to ~~either claims 21 or 22~~ claim 21 wherein the polymer matrix is a biodegradable polymer matrix.

24. (Original) A micro particle composition according to claim 23 wherein the polymer matrix biodegrades to after one to three months following introduction into a patient.

25. (Currently Amended) A micro particle composition according to ~~anyone of claims 1 to 24~~ claim 1 wherein the micro particles in the composition are adapted for site specific delivery to or accumulation within a tissue in a patient.

26. (Currently Amended) A microparticle composition according to ~~anyone of claims 1 to 25~~ claim 1 wherein the composition includes pharmaceutically acceptable carriers and or diluents.

27. (Currently Amended) A micro particle composition according to ~~anyone of claims 1 to 26~~ claim 1 wherein the microparticles in the composition also include bioactive,

chemical or radioactive agents that are capable of delivering a therapeutic effect to a patient.

28. (Currently Amended) A method for heating a target site in a patient including the steps of:

- (i) administering a microparticle composition according to ~~any one of claims 22 to 27~~ claim 22 to a target site in a patient; and
- (ii) exposing the target site to an alternating magnetic field, of a clinically acceptable frequency and strength,

wherein the combination of the alternating magnetic field with the micro particle composition induces heat within the target site.

29. (Original) The method according to claim 28 wherein the microparticles are of a size and density that permits the transport of the microparticle composition to the capillary beds supplying the target site.

30. (Original) The method according to claim 28 wherein the alternating magnetic field is operated at a frequency in the range of about 50-300 kHz and field strength of about 60-120 Oe.

31. (Original) The method according to claim 30 wherein the alternating magnetic field is operated at a frequency of about 100 kHz and a field strength of about 90 Oe.

32. (Currently Amended) The use of a micro particle composition according to ~~anyone~~
~~of claims 1 to 27~~ claim 1 in the manufacture of a medicament for the treatment of
diseased tissue.

33. (Original) A micro particle preparation comprising nanomagnetic particles distributed
within a matrix, wherein the microparticles within the preparation have at least one of the
following properties: (a) a VAR of at least about 1 Watts/cm³ under alternating magnetic
field conditions suitable for use in a patient; (b) a density of about 2.7 or less; or (c) a size
range of about 100 nm to about 200 microns.

34. (Original) The use of a micro particle preparation according to claim 33 in the
manufacture of a medicament for the treatment of diseased tissue.